


KPS-5 (PPS)

Potassium peroxydisulfate (potassium persulfate) with 0.5 % silicic acid
CAS#7727-21-1
Technically pure, solid

Structural Formula



Description

Potassium persulfate is a white, finely crystalline, odourless salt consisting of technically pure potassium peroxydisulfate and silicic acid to enhance the free flowing properties. It is used as an initiator (source of free radicals) for the polymerisation of monomers and as a strong oxidising agent in many applications. It has the particular advantage of being only slightly hygroscopic and easy and safe to handle. As a result of the process used for its production it is free from contamination by ammonium ions. As a result of its extremely high purity it has a good storage stability. Due to its fine crystallinity potassium peroxydisulfate tends to lumping.

Technical Data

Appearance	white, finely crystalline solid
Assay (typically)	approx. 99.0 % w/w
Active oxygen (AO, typically)	approx. 5.9 % w/w
Acid (calculated as H ₂ SO ₄ , typically)	approx. 0.05 % w/w
Iron content (typically)	approx. 1 mg/kg
Bulk density	approx. 1100 kg/m ³
Melting point	(decomposition)
Solubility in water at 10 / 20 / 40 / 60 °C	approx. 30 / 50 / 105 / 210 g/L
pH of a 1 % solution in water (typically)*	approx. 4.0
pH of a 10 % solution in water (typically)*	approx. 3.3
Decomposition temperature (SADT)**	170 °C
Recommended storage temperature	< 30 °C
Storage stability as from date of delivery	12 months
Moisture content (typically)	< 0.03 % w/w

*The initial pH value depends on the certified sulfuric acid content.

**Even small amounts of moisture or impurities can noticeably reduce SADT.

Standard Packaging

25 kg PE-bag
1000 kg big bag

Application

POLYMERIZATION:

Initiator for the emulsion or solution polymerization of acrylic monomers, vinyl acetate, vinyl chloride etc. and for the emulsion copolymerization of styrene, acrylonitrile, butadiene etc.

Dosage: 0.1 - 0.5 % KPS-5 (PPS)

Temperature: 75 - 95 °C

In combination with redox systems (ascorbic acid, Rongalite, sulfites or sugar - possibly in combination with heavy metal salts such as Fe²⁺) it can also be used for polymerization reactions carried out at lower - and even at ambient temperatures. To reduce the residual monomer content, a combination of KPS-5 (PPS) with TBHP-70-AQ is recommended, particularly in cases where redox systems are used.

COSMETICS:

- Essential component of bleaching formulations

PAPER:

- Modification of starch; repulping particularly of wet-strength paper

TEXTILE:

- Desizing agent and bleach activator - particularly for cold bleaching (e.g. bleaching of jeans).

OTHERS:

- Chemical synthesis
- Water treatment (decontamination)
- Waste gas treatment; oxidative degradation of harmful substances (e.g. Hg)

Storage

Avoid any source of heat, light, humidity and protect the product from impurities. Keep dry and within safe temperature limits.

Disclaimer:

The information contained herein and all further technical advice that may be provided by United Initiators reflects our current knowledge and experience based on our internal research and development as to our products and applications. United Initiators does not make any warranties about the information provided as to specific properties of products described, their suitability for a particular application and representing complete instructions for use. Additionally, United Initiators does not make any warranties in respect of product and shelf life properties. We are not legally responsible and liable for the use of any information provided, including with regard to existing third party intellectual property rights, especially patent rights. We reserve the right to make any changes according to technological progress or further developments. Application and usage of our products based on our technical advice is out of our control, strictly at your own risk and is the sole responsibility of the user. The user is not released from the obligation to conduct careful inspection and testing of incoming products in order to verify their suitability for the intended application.

United Initiators
Europe
T: +49 89 74422 237
F: +49 89 74422 6237
cs-initiators.eu@united-in.com

United Initiators
Nafta
T: +1 800 231 2702
F: +1 440 323 0898
cs-initiators.nafta@united-in.com

United Initiators
China
T: +86 21 6117 2760
F: +86 139 2503 8952
cs-initiators.cn@united-in.com

United Initiators
Australia
T: +61 2 9316 0046
F: +61 2 9316 0034
cs-initiators.au@united-in.com

www.united-initiators.com